

# Asymmetric Miyaura–Michael Reaction with Polymeric Rh/Ag Catalysts

Category

Polymer-Supported Synthesis


Key words

bimetallic nanoparticle catalysts



rhodium

silver

asymmetric 1,4-addition



## Asymmetric 1,4-addition with PI/CB Rh/Ag catalyst 2:



**Significance:** Polystyrene-based polymer-incarcerated bimetallic rhodium nanoparticle catalysts PI/CB Rh/Ag **2a–b** were prepared from co-polymer **1**, carbon black (CB), [Rh(OAc)<sub>2</sub>]<sub>2</sub>, and AgSbF<sub>6</sub>. Asymmetric 1,4-addition of arylboronic acids to enones was carried out with **2** and chiral ligand **3** to give the corresponding ketones in 70–99% yield with 74–98% ee without leaching of rhodium.

**Comment:** Catalyst **2a** was reused 13 times for the reaction of phenylboronic acid with 2-cyclohexenone. After the 10<sup>th</sup> use, the recovered catalyst was heated at 170 °C to regain its catalytic activity (1<sup>st</sup>–8<sup>th</sup> use: >94% yield, 9<sup>th</sup> use: 67% yield, 10<sup>th</sup> use: 60% yield, 11<sup>th</sup>–14<sup>th</sup> use: >90% yield, with 98% ee in all cycles).

**SYNFACTS Contributors:** Yasuhiro Uozumi, Yoichi M. A. Yamada, Yoshinari Yuyama  
 Synfacts 2013, 9(1), 0115 Published online: 17.12.2012  
 DOI: 10.1055/s-0032-1317915; Reg-No.: Y14312SF